

产品技术指标
Technical Specifications of Labelstock

代号 Product Code	AM360		
产品结构 Label construction	80g 铜版纸/GH502/白格 80gsm Semi-gloss Art Paper/GH502/White Glassine		
面材 Facestock	80g 铜版纸 80gsm Semi-gloss Art Paper		
胶水 Adhesive	GH502		
底材 Liner	58g/m ² 白色格拉辛纸 58gsm White Glassine		
技术指标 Items	Specifications	单位 Unit	方法 Test Method
面材 Facestock			
厚度 Caliper	68±10%	μm	GB/T 451.3-2003
克重 Basic Weight	80±10%	%	GB/T 451.2-2002
白度 Brightness	≥88	%	GB/T 7974-2002
光泽度 Glossiness	67±5	-	HUNTER 75°
<p>本产品面材经过超级研光处理，表面光滑，白度高，主推荐空白模切。 The face stock is a super calendered semi-gloss white coated paper. It has optimized opacity brightness, smoothness, glossiness. Mainly recommend to use for general application and blank die-cutting.</p>			
胶粘剂 Adhesive			
初粘力 'Loop' Tack	≥14 or PT	N/25mm	FTM9, ss
90° 剥离力 (20min) Peel Adhesion (90°)	≥6 or PT	N/25mm	FTM2, ss
最低标贴温度 Minimum Application Temp.	10℃		
使用温度 Service Temp.	-15℃ — +65℃		

本产品采用通用型热熔胶，具有较高的初粘性，在诸多包装材料上均有优异的表现性能。不适合在 PVC 表面上应用。不推荐小口径及不规则表面或经常挤压的瓶体，使用前须在最终使用环境下进行全面的贴标测试。

This product uses general hot melt adhesive, the initial viscosity and the final stickiness are high, it has excellent performance on various packing materials. This product is not suitable for PVC surface. Not recommend applying on irregular surface or bottle which is squeezed frequently. Labeling testing is always recommended before production.

底材

Liner

克重 Basic Weight	58±10%	gsm	GB/T 451.2-2002
厚度 Caliper	53±10%	µm	GB/T 451.3-2003
纵向抗张强度 Tensile Strength (MD)	≥ 5.0	kN/m	GB/T 12914-2018

印刷及加工

Printing & Converting

- ◇ 适合用于胶版、凹版、柔版多种印刷方式。
Applicable for offset, intaglio, flexographic printing, etc.
- ◇ 不推荐精美图案及满版实地印刷。
Not recommended for exquisite pictures and full version printing.
- ◇ 应注意控制油墨的粘度，避免过粘的油墨造成涂层的脱落。
Avoid the coating peeled off by controlling ink's viscosity not too thick.
- ◇ 优异的纸张加工性能，适合轮转及平式的加工方式。
Extremely good performance on processing, Applicable for rotary and plate process.
- ◇ 适合烫金工艺。
Extremely good performance on gold blocking.
- ◇ 应避免复卷张力过大，导致标签溢胶。
To avoid adhesive oozing from the label edge, tension should be controlled during rewinding.
- ◇ 印刷前建议对油墨先行测试。
It is recommended to test the ink before printing .

Storage & Preservation

- ◇ 在温度 23±2℃、相对湿度 50±5%的情况下，有效期为 1 年。超过有效期的产品，经检验合格仍可使用。
One year when stored at 23±2℃ and 50±5% RH. If test qualified, the label can continually been used after shelf life.

特别说明 (Note) :

1. 冠豪所有有关材料的说明、技术信息及使用推荐是基于我们认为可信的测试结果，但不构成一种担保。
All relative materials' description, technical specification and usage recommendation are based upon tests believed to be reliable but do not represent a guarantee.
2. 由于产品的使用条件和加工条件不同，在使用之前请测试，避免未知的风险。
Test before production to avoid potential risks, due to various operating environment and processing conditions.
3. 技术文件以冠豪现行条款为准,本出版物将替代之前的所有版本。我方有权更改所有信息，恕不另行通知。
Guanhao reserves the right to interpret latest terms to the technical documents.

Contact Us

浙江冠豪新材料有限公司
ZHEJIANG GUANHAO FUNCTIONAL MATERIAL CO.,LTD
浙江省平湖市新仓镇仓庆路 888 号
NO.888 CANGQING RD XINCANG PINGHU ZHEJIANG CHINA
网址 (Website) : <http://www.guanhao.com>
E-mail: guanhao@guanhao.com

