

**产品技术指标**  
**Technical Specifications of Labelstock**

<b>代号</b> <b>Product Code</b>	S8MG3		
<b>产品结构</b> <b>Label construction</b>	95um 热敏膜/GH505/白格 95um Thermal PP Film/GH505/White Glassine		
<b>面材</b> <b>Facestock</b>	95um 热敏膜 95um Thermal PP Film		
<b>胶水</b> <b>Adhesive</b>	GH505		
<b>底材</b> <b>Liner</b>	58g/m <sup>2</sup> 白格拉辛纸 58gsm White Glassine		
<b>技术指标</b> <b>Items</b>	<b>Specifications</b>	<b>单位</b> <b>Unit</b>	<b>方法</b> <b>Test Method</b>
<b>面材</b> <b>Facestock</b>			
<b>厚度</b> <b>Caliper</b>	95±10%	μm	GB/T 451.3-2003
<b>克重</b> <b>Basic Weight</b>	72±10%	%	GB/T 451.2-2002
<b>白度</b> <b>Brightness</b>	≥85	%	GB/T 7974-2002
<b>防水</b> <b>Water Resistance</b>	≥80	%	GB/T 28210-2011
<b>防油</b> <b>Oil Resistance</b>	≥80	%	GB/T 28210-2011
<b>防酒精</b> <b>Alcohol Resistance</b>	≥70	%	GB/T 28210-2011
<b>显色光密度</b> <b>Dynamic Sensitivity</b>	≥1.00	-	GB/T 28210-2011
<p>本产品采用具有防水、防油、防酒精性能的膜基热敏作面材，耐撕裂，耐摩擦，适用于航空或铁路行李标签、高品质物流标签等。</p> <p>The thermal top coating has good feature of water resistance, oil resistance, alcohol resistance with excellent scratch resistance. Suitable for air or rail baggage label, high quality logistics label, etc.</p>			
<b>胶粘剂</b> <b>Adhesive</b>			
<b>初粘力</b> <b>'Loop' Tack</b>	≥14	N/25mm	FTM9, ss
<b>90° 剥离力 (20min)</b> <b>Peel Adhesion (90°)</b>	≥8	N/25mm	FTM2, ss
<b>最低标贴温度</b> <b>Minimum Application Temp.</b>	10℃		

<b>使用温度</b> <b>Service Temp.</b>	<b>-15℃ — +65℃</b>		
<p>本产品采用通用型热熔胶，具有较高的初粘性，在诸多包装材料上均有优异的表现性能。不适合在 PVC 表面上应用。不推荐小口径及不规则表面或经常挤压的瓶体，使用前须在最终使用环境下进行全面的贴标测试。</p> <p>This product uses general hot melt adhesive, the initial viscosity and the final stickiness are high, it has excellent performance on various packing materials. This product is not suitable for PVC surface. Labeling testing is always recommended before production.</p>			
<b>底材</b> <b>Liner</b>			
<b>克重</b> <b>Basic Weight</b>	<b>58±10%</b>	<b>gsm</b>	<b>GB/T 451.2-2002</b>
<b>厚度</b> <b>Caliper</b>	<b>53±10%</b>	<b>µm</b>	<b>GB/T 451.3-2003</b>
<b>纵向抗张强度</b> <b>Tensile Strength (MD)</b>	<b>≥ 5.0</b>	<b>kN/m</b>	<b>GB/T 12914-2018</b>
<b>印刷及加工</b> <b>Printing &amp; Converting</b>			
<ul style="list-style-type: none"> <li>◇ 本产品适用于多数传统印刷方式。 This product is suitable for most traditional printing methods..</li> <li>◇ 由于产品的热敏特性，应避免超过 50℃ 的加工环境。 Due to the heat sensitivity of the product, the processing environment exceeding 50℃ should be avoided .</li> <li>◇ 运输加工过程注意减少材料摩擦与碰撞，以避免出现外圈或局部蹭黑现象发生。 During the transportation process, we should pay attention to reducing the friction and collision of materials, so as to avoid the occurrence of outer ring or local blackening.</li> <li>◇ 含酒精或挥发性有机溶剂的油墨可能对热敏层产生破坏。 Ink containing alcohol or volatile organic solvents may damage the heat sensitive layer.</li> <li>◇ 用于柔性版印刷时，推荐使用 UV 或水性油墨及光油。 UV or water-based ink and varnish are recommended for flexographic printing.</li> <li>◇ 印刷前建议对油墨先行测试。 It is recommended to test the ink before printing .</li> </ul>			
<b>Storage &amp; Preservation</b>			
<ul style="list-style-type: none"> <li>◇ 在温度 23±2℃、相对湿度 50±5% 的情况下，有效期为 1 年。超过有效期的产品，经检验合格仍可使用。 One year when stored at 23±2℃ and 50±5% RH. If test qualified, the label can continually been used after shelf life.</li> </ul>			

特别说明 (Note) :

1. 冠豪所有有关材料的说明、技术信息及使用推荐是基于我们认为可信的测试结果，但不构成一种担保。  
All relative materials' description, technical specification and usage recommendation are based upon tests believed to be reliable but do not represent a guarantee.
2. 由于产品的使用条件和加工条件不同，在使用之前请测试，避免未知的风险。  
Test before production to avoid potential risks, due to various operating environment and processing conditions.
3. 技术文件以冠豪现行条款为准,本出版物将替代之前的所有版本。我方有权更改所有信息，恕不另行通知。  
Guanhao reserves the right to interpret latest terms to the technical documents.

Contact Us  
 浙江冠豪新材料有限公司  
 ZHEJIANG GUANHAO FUNCTIONAL MATERIAL CO.,LTD  
 浙江省平湖市新仓镇仓庆路 888 号  
 NO.888 CANGQING RD XINCANG PINGHU ZHEJIANG CHINA  
 网址 (Website) : <http://www.guanhao.com>  
 E-mail: [guanhao@guanhao.com](mailto:guanhao@guanhao.com)

