

**产品技术指标**  
**Technical Specifications of Labelstock**

<b>代号</b> <b>Product Code</b>	G7		
<b>产品结构</b> <b>Label construction</b>	81g 白格离型纸 81gsm White Glassine		
<b>底材</b> <b>Liner</b>	80g 白格 80gsm White Glassine		
<b>技术指标</b> <b>Items</b>	<b>Specifications</b>	<b>单位</b> <b>Unit</b>	<b>方法</b> <b>Test Method</b>
<b>底材</b> <b>Liner</b>			
<b>定量</b> <b>Basis Weight</b>	80±10%	g/m <sup>2</sup>	GB/T 451.2-2002
<b>厚度</b> <b>Caliper</b>	70±10%	μm	GB/T 451.3-2003
<b>纵向抗张强度</b> <b>Tensile Strength (MD)</b>	≥6.5	kN/m	GB/T 12914-2018
<p>本产品底材经过超级压光处理，表面光滑，力学强度高。                      The substrate of this product is super calendered, with smooth surface and high mechanical strength.</p>			
<b>硅油</b> <b>Silicon oil</b>			
<b>涂硅量</b> <b>Silicon coating amount</b>	1.0±0.2	g/m <sup>2</sup>	/
<b>0.3m/min 离型力</b> (Tesa7475 胶带) <b>0.3m/min Release force</b> (Tesa7475 胶带)	8~20	g/25mm	FTM3, ss
<p>本产品采用无溶剂型硅油涂布，离型力适中，适合搭配热熔型、水性压敏胶，使用前需针对应用进行全面的离型力性能测试。                      This product is coated with solvent-free silicone oil, which has moderate release force and is suitable for matching with hot-melt and water-based pressure-sensitive adhesives. Before use, a comprehensive release force performance test should be carried out for the application.</p>			
<b>印刷及加工</b> <b>Printing &amp; Converting</b>			
<p>◇ 本产品常作为不干胶标签底纸与胶黏剂及面材进行涂布复合加工，背面可进行简单印刷，印刷前建议对油墨先行测试。                      This product is often used as a backing paper for self-adhesive labels, coated with adhesives and surface materials, and can be printed simply on the back. It is recommended to test the ink before printing.</p>			
<b>Storage &amp; Preservation</b>			
<p>◇ 在温度 23±2℃、相对湿度 50±5%的情况下，有效期为 1 年。超过有效期的产品，经检验合格仍可使用。                      One year when stored at 23±2℃ and 50±5% RH. If test qualified, the label can continually been used after shelf life.</p>			

特别说明 (Note) :

1. 冠豪所有有关材料的说明、技术信息及使用推荐是基于我们认为可信的测试结果，但不构成一种担保。  
All relative materials' description, technical specification and usage recommendation are based upon tests believed to be reliable but do not represent a guarantee.
2. 由于产品的使用条件和加工条件不同，在使用之前请测试，避免未知的风险。  
Test before production to avoid potential risks, due to various operating environment and processing conditions.
3. 技术文件以冠豪现行条款为准,本出版物将替代之前的所有版本。我方有权更改所有信息，恕不另行通知。  
Guanhao reserves the right to interpret latest terms to the technical documents.

Contact Us

浙江冠豪新材料有限公司  
ZHEJIANG GUANHAO FUNCTIONAL MATERIAL CO.,LTD  
浙江省平湖市新仓镇仓庆路 888 号  
NO.888 CANGQING RD XINCANG PINGHU ZHEJIANG CHINA  
网址 (Website): <http://www.guanhao.com>  
E-mail: [guanhao@guanhao.com](mailto:guanhao@guanhao.com)

