

产品技术指标
Technical Specifications of Labelstock

代号 Product Code	S9153A		
产品结构 Label construction	75um 热敏膜/GH502/白格 75um Thermal PP Film/GH502/White Glassine		
面材 Facestock	75um 热敏膜 75um Thermal PP Film		
胶水 Adhesive	GH502		
底材 Liner	58g/m ² 白格拉辛纸 58gsm White Glassine		
技术指标 Items	Specifications	单位 Unit	方法 Test Method
面材 Facestock			
厚度 Caliper	75±10%	μm	GB/T 451.3-2003
克重 Basic Weight	57±10%	%	GB/T 451.2-2002
白度 Brightness	≥85	%	GB/T 7974-2002
防水 Water Resistance	≥80	%	GB/T 28210-2011
防油 Oil Resistance	≥80	%	GB/T 28210-2011
显色光密度 Dynamic Sensitivity	≥1.00	-	GB/T 28210-2011
<p>面材为采用具有防水、防油的膜基热敏，对水、油有一定防护作用，白度高，耐撕裂，耐摩擦，适用于物流标签等。 The thermal top coating has good feature of water resistance, oil resistance, alcohol resistance and with excellent scratch resistance. Have a good thermal image preservation. Suitable for logistics label, etc.</p>			
胶粘剂 Adhesive			
初粘力 'Loop' Tack	≥14	N/25mm	FTM9, ss
90° 剥离力 (20min) Peel Adhesion (90°)	≥7	N/25mm	FTM2, ss
最低标贴温度 Minimum Application Temp.	10℃		
使用温度 Service Temp.	-15℃ — +65℃		

本产品采用通用型热熔胶，具有较高的初粘性，在诸多包装材料上均有优异的表现性能。不适合在 PVC 表面上应用。不推荐小口径及不规则表面或经常挤压的瓶体，使用前须在最终使用环境下进行全面的贴标测试。
 This product uses general hot melt adhesive, the initial viscosity and the final stickiness are high, it has excellent performance on various packing materials. This product is not suitable for PVC surface. Not recommend applying on irregular surface or bottle which is squeezed frequently. Labeling testing is always recommended before production.

底材

Liner

克重 Basic Weight	58±10%	gsm	GB/T 451.2-2002
厚度 Caliper	53±10%	µm	GB/T 451.3-2003
纵向抗张强度 Tensile Strength (MD)	≥ 5.0	kN/m	GB/T 12914-2018

印刷及加工

Printing & Converting

- ◇ 本产品适合于多数传统印刷方式。
This product is suitable for most traditional printing methods..
- ◇ 由于产品的热敏特性，应避免超过 50℃ 的加工环境。
Due to the heat sensitivity of the product, the processing environment exceeding 50℃ should be avoided .
- ◇ 运输加工过程注意减少材料摩擦与碰撞，以避免出现外圈或局部蹭黑现象发生。
During the transportation process, we should pay attention to reducing the friction and collision of materials, so as to avoid the occurrence of outer ring or local blackening.
- ◇ 含酒精或挥发性有机溶剂的油墨可能对热敏层产生破坏。
Ink containing alcohol or volatile organic solvents may damage the heat sensitive layer.
- ◇ 用于柔性版印刷时，推荐使用 UV 或水性油墨及光油。
UV or water-based ink and varnish are recommended for flexographic printing.
- ◇ 印刷前建议对油墨先行测试。
It is recommended to test the ink before printing .

Storage & Preservation

- ◇ 在温度 23±2℃、相对湿度 50±5% 的情况下，有效期为 1 年。超过有效期的产品，经检验合格仍可使用。
One year when stored at 23±2℃ and 50±5% RH. If test qualified, the label can continually been used after shelf life.

特别说明 (Note) :

1. 冠豪所有有关材料的说明、技术信息及使用推荐是基于我们认为可信的测试结果，但不构成一种担保。
All relative materials' description, technical specification and usage recommendation are based upon tests believed to be reliable but do not represent a guarantee.
2. 由于产品的使用条件和加工条件不同，在使用之前请测试，避免未知的风险。
Test before production to avoid potential risks, due to various operating environment and processing conditions.
3. 技术文件以冠豪现行条款为准,本出版物将替代之前的所有版本。我方有权更改所有信息，恕不另行通知。
Guanhao reserves the right to interpret latest terms to the technical documents.

